

# FLEXURAL STRENGTH TEST OF PRETTAU® ANTERIOR®

---

Zirkonzahn (13/08/2014)

Flexural strength test of Prettau® Anterior®

## ABSTRACT

According to a test procedure for determining the flexural strength conducted by Zirkonzahn, Prettau® Anterior® has been able to achieve a flexural strength of 670 MPa. In an independently conducted study, carried out at the University of Pennsylvania, approximately the same results have been obtained.

|                          |                       |
|--------------------------|-----------------------|
| Material:                | Prettau® Anterior® T0 |
| Flexural Strength (MPa): | 670,0                 |

---

Zirkonzahn GmbH/Srl  
Head of Product Management  
Julian Steger



Zirkonzahn GmbH/Srl  
Head of Research and Development  
Manuel Hellweger

